

Vydyne 21SPC is a general-purpose, unfilled, lubricated, PA66 resin. Designed principally for injection-molding fabrication, this product offers a combination of engineering properties characterized by high strength; rigidity; good toughness; high melt point; good surface lubricity; abrasion resistance; and resistance to many chemicals, machine and motor oils, solvents and gasoline

General

Additive	• Lubricant
Features	<ul style="list-style-type: none"> • Abrasion Resistance • Gasoline Resistant • Good Toughness • Lubricated • Chemical Resistant • General Purpose • High Rigidity • Oil Resistant • Fast Molding Cycle • Good Mold Release • High Strength • Solvent Resistant
Agency Rating	<ul style="list-style-type: none"> • ASTM, D4066 PA0111 • EU, 10/2011 • FED, L-P-410A • SAE, J1639 PA0121 Z6 • ASTM, D6779 PA0111 • EU, 2023/2006 • MIL, M-20693B • EC, 1935/2004 • FDA, 21 CFR 177.1500 • NSF, STD-51
Automotive Specifications	<ul style="list-style-type: none"> • Aisin TO20141124 - P-PA66-N-011 • Renault UB15b • Toyota TSM5516G, Class 2, Rev 9 (compliance)
Resin Identification	• PA66 - ISO 1043
UL File Number	• E70062
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	dry	cond.	Unit	Test Standard
Density	1.14	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.7	*	%	
Flow : 23°C, 2.00 mm	1.8	*	%	
Water Absorption				ISO 62
23°C, 24 hr	1.2	*	%	
Equilibrium, 23°C, 50% RH	2.4	*	%	
Outdoor Suitability	f2			UL 746C

Mechanical	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	2800	1800	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	86	56	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	56	46	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	4.8	22	%	ISO 527-2
Tensile Strain (Break, 23°C)	23	87	%	ISO 527-2

©2026 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Flexural Modulus (23°C)	2900	1500	MPa	ISO 178
Flexural Strength (23°C)	80	50	MPa	ISO 178
Poisson's Ratio (23°C)	0.4			ISO 527-2

Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	6	20	kJ/m²	
-30°C	5	7	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	N	N	kJ/m²	
-30°C	N	N	kJ/m²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	6	20	kJ/m²	
-30°C	5	7	kJ/m²	

Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	70	-	°C	
0.45 MPa, Unannealed	200	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	100	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	100	*	E-6/K	
RTI Elec				UL 746
0.400 mm	130		°C	
0.710 mm	130		°C	
1.50 mm	130		°C	
3.00 mm	130		°C	
RTI Imp				UL 746
0.400 mm	75		°C	
0.710 mm	75		°C	
1.50mm	75		°C	
3.00 mm	75		°C	
RTI Str				UL 746
0.400 mm	75		°C	
0.710 mm	85		°C	
1.50 mm	85		°C	
3.00 mm	85		°C	

Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E11	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	26	-	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	5			ASTM D 495
High Amp Arc Ignition (HAI)				UL 746
0.400 mm	PLC 1			
0.710 mm	PLC 0			
1.50 mm	PLC 0			
3.00 mm	PLC 0			
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 0			UL 746
Hot-wire Ignition (HWI)				UL 746
0.400 mm	PLC 4			
0.710 mm	PLC 4			
1.50 mm	PLC 3			
3.00 mm	PLC 2			
Flammability	dry	cond.	Unit	Test Standard
Flammability				UL 94
0.400 mm	V-2			
0.710 mm	V-2			
1.50 mm	V-2			
3.00 mm	V-2			
Glow Wire Flammability Index				IEC 60695-2-12
0.400 mm	960		°C	
0.710 mm	960		°C	
1.50 mm	960		°C	
3.00 mm	960		°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.400 mm	825		°C	
0.710 mm	850		°C	
1.50 mm	850		°C	
3.00 mm	850		°C	
Oxygen index	25	*	%	EN ISO 4589-2
Railway Application	dry	cond.	Unit	Test Standard
Oxygen index	25	-	%	EN ISO 4589-2

Injection	Value	Unit
Drying Temperature	70	°C
Drying Time	1 - 3	h
Rear Temperature	260 - 280	°C
Middle Temperature	270 - 285	°C
Front Temperature	280 - 290	°C
Nozzle temperature	280 - 300	°C
Processing (Melt) Temperature	285 - 300	°C
Mold Temperature	65 - 95	°C



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof. Material is produced at multiple production sites with differing specification approvals.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.