

Vydyne 41 NT is a general-purpose, high impact-modified PA66 resin. The product is recognized for all the processing and property advantages inherent to PA66 with the addition of improved impact strength. This resin offers a well balanced combination of engineering properties characterized by high melt point, good surface lubricity, abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline. 41 NT is designed to meet the critical low-temperature impact requirements called out in many automotive specifications.

General

Features	<ul style="list-style-type: none"> • Abrasion Resistance • Good Processability • Oil Resistant 	<ul style="list-style-type: none"> • Chemical Resistant • High Impact Resistance • Solvent Resistant 	<ul style="list-style-type: none"> • Gasoline Resistant • Low Temperature Impact Resistance
Agency Rating	• ASTM, D4066 PA0171	• ASTM, D6779 PA0171	
Automotive Specifications	• Aisin TO20141124 - P-PA66-N-508		
Resin Identification	• PA66-I - ISO 1043		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	dry	cond.	Unit	Test Standard
Density	1.08	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.6	*	%	
Flow : 23°C, 2.00 mm	1.8	*	%	
Water Absorption				ISO 62
23°C, 24 hr	1	*	%	
Equilibrium, 23°C, 50% RH	2.1	*	%	

Mechanical	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	2200	1400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	50	35	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	43	39	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	50	175	%	ISO 527-2
Flexural Modulus (23°C)	1800	500	MPa	ISO 178
Flexural Strength (23°C)	53	17	MPa	ISO 178

Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	76	110	kJ/m ²	
-30°C	35	25	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	N	N	kJ/m ²	
-30°C	N	N	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	78	88	kJ/m ²	
-30°C	40	29	kJ/m ²	
Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	58	-	°C	
0.45 MPa, Unannealed	145	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	168	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	149	*	E-6/K	
RTI Elec				UL 746
0.750 mm	125		°C	
1.50 mm	125		°C	
3.00 mm	125		°C	
RTI Imp				UL 746
0.750 mm	75		°C	
1.50mm	75		°C	
3.00 mm	75		°C	
RTI Str				UL 746
0.750 mm	85		°C	
1.50 mm	85		°C	
3.00 mm	85		°C	
Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E9	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	26	-	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	5			ASTM D 495
Comparative Tracking Index (3.00 mm)	600		V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746

0.750 mm	PLC 0	
1.50 mm	PLC 0	
3.00 mm	PLC 0	
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 0	UL 746
Hot-wire Ignition (HWI)		UL 746
0.750 mm	PLC 4	
1.50 mm	PLC 3	
3.00 mm	PLC 3	

Flammability	Value	Unit	Test Standard
Flammability			UL 94
0.750 mm	HB		
1.50 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
0.400 mm	750	°C	
0.750 mm	700	°C	
1.50 mm	700	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.400 mm	775	°C	
0.750 mm	725	°C	
1.50 mm	725	°C	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C
Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C
Mold Temperature	65 - 95	°C



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

©2026 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof. Material is produced at multiple production sites with differing specification approvals.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.