

Vydyne R530H NT is a general purpose, 30% glass-filled, heat-stabilized PA66 based resin designed for injection molding applications. R530H NT offers improved flow with a natural surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

General

Additive	• Heat Stabilizer	• Lubricant	
Features	• Antifreeze Resistant • Gasoline Resistant • Lubricated	• Chemical Resistant • Good Flow • Solvent Resistant	• Fatigue Resistant • Heat Stabilized
Agency Rating	• ASTM, D4066 PA012G30 • EU, 2023/2006	• ASTM, D6779 PA012G30 • EU, 10/2011	• FDA, 21 CFR 177.1500 • EC, 1935/2004
Automotive Specifications	• GM GMW3038P-PA66-GF30J • Tesla TM-1006 v3 - 101130 • Mahle SD2-181 (AR.06576) Rev. 7 • GM GMW16270P-PA66-GF30 • Aisin TO20141124 - P-PA66-GF30-807	• Tesla TM-1006 v3 - 301130 • Stellantis MS-DB-41 CPN 4818 • HMG MS211-42 Type A • Ford WSS-M4D752-B1 • Toyota TSM5603G, Class 2B, Rev 5 (compliance)	• Tesla TM-1006 v3 - 201130 • Mahle SD2-181 (AR.06576) Rev. 7 • GM GMW3038P-PA66-GF30H • Chery Motor Q-SQR.S1-33-2012 CMP.PA66.G6
Resin Identification	• PA66-GF30 - ISO 1043		
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	dry	cond.	Unit	Test Standard
Density	1.37	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.2	*	%	
Flow : 23°C, 2.00 mm	0.5	*	%	
Water Absorption, 23°C, 24 hr	1.2	*	%	ISO 62

Mechanical	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	10000	7400	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	195	135	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3	5	%	ISO 527-2
Flexural Modulus (23°C)	9500	8100	MPa	ISO 178

©2026 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Flexural Strength (23°C)	272	208	MPa	ISO 178
Poisson's Ratio (23°C)	0.37			ISO 527-2

Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	13	14	kJ/m ²	
-30°C	12	11	kJ/m ²	
-40°C	12	11	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	72	90	kJ/m ²	
-30°C	63	67	kJ/m ²	
-40°C	61	64	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	11	13	kJ/m ²	
-30°C	11	11	kJ/m ²	
-40°C	11	11	kJ/m ²	

Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	252	250	°C	
0.45 MPa, Unannealed	262	261	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	22	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	76	*	E-6/K	
RTI Elec				UL 746
0.750 mm	140		°C	
1.50 mm	140		°C	
3.00 mm	140		°C	
RTI Imp				UL 746
0.750 mm	120		°C	
1.50mm	120		°C	
3.00 mm	120		°C	
RTI Str				UL 746
0.750 mm	125		°C	
1.50 mm	140		°C	
3.00 mm	140		°C	

Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E11	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	20	-	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	6			ASTM D 495
Comparative Tracking Index (3.00 mm)	250 - 399		V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0			
1.50 mm	PLC 0			
3.00 mm	PLC 0			
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 1			UL 746
Hot-wire Ignition (HWI)				UL 746
0.750 mm	PLC 4			
1.50 mm	PLC 3			
3.00 mm	PLC 4			

Flammability	Value	Unit	Test Standard
Burning Rate, 2.00 mm		mm/min	ISO 3795
Flammability			UL 94
0.750 mm	HB		
1.50 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	675	°C	
1.50 mm	675	°C	
3.00 mm	675	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	700	°C	
1.50 mm	700	°C	
3.00 mm	700	°C	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C
Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C

Mold Temperature

65 - 95

°C



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof. Material is produced at multiple production sites with differing specification approvals.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.